

July, 2011

## 3M™ Double Coated Tape 9731

### Product Description

3M™ Double Coated Tapes 9731 has a firm, silicone pressure sensitive adhesive coated on one side of a polyester film carrier and a high performance acrylic adhesive coated on the other side of the carrier.



### Product Features

- Silicone adhesive provides good bond to Silicone Rubber, strong holding power to various silicone surfaces, good temperature performance and good solvent resistance.
- 3M™ Adhesive 350 provides very high adhesion to a wide variety of materials, excellent shear holding power, high temperature resistance and excellent UV resistance.
- A thin polyester carrier provides dimensional stability and improved handling with ease of die cutting and lamination compared to adhesive transfer tapes.

**Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

**Typical Physical Properties**

Property	Values		Method	Notes	Test Name
Total Tape Thickness	5.5 mil	0.14 mm	ASTM D3652		
Carrier Thickness	1 mil	0.025 mm			
Liner Print	None				
Liner Thickness	4.2 mil	0.17 mm			
Primary Liner Thickness	4.2 mil	0.17 mm			
Secondary Liner Thickness	2.9 mil	0.07 mm			
Adhesive Carrier	Clear PET (Polyester)				
Primary Liner Type	58# Polycoated Kraft			Inner liner is primary (stays with die-cut part); Outer liner is secondary (removed first)	
Liner Color	Tan				Primary
Secondary Liner Type	Fluoropolymer non-Silicone			Inner liner is primary(stays with die-cut part); Outer liner is secondary (removed first)	
Liner Color	Clear				Secondary

Adhesive Thickness		Test Name	Notes
2.9 mil		Backside	Backside adhesive is on the exterior of the roll, exposed when liner is removed.
0.041 mm	1.6 mil	Faceside	Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
0.07 mm		Backside	The caliper listed is based on a calculation from manufacturing controlled adhesive coat weight. While past data pages have listed nominal thicknesses of 1 and 2 mils, the coat weight (and theoretical caliper) has not changed.

Property: Adhesive Thickness

**Typical Physical Properties (continued)**

Adhesive Type	Test Name	Notes
350 Acrylic Adhesive	Faceside	Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
Silicone Adhesive	Backside	Backside adhesive is on the exterior of the roll, exposed when liner is removed.

Property: Adhesive Type

**Adhesive Type**

Silicone  
Acrylic

**Liner**

PCK  
PET

**Typical Performance Characteristics**

180° Peel Adhesion		Test Name	Substrate	Dwell/Cure Time	Dwell Time Units	Temp C	Temp F
8.1 N/cm	74 oz/in	350 Acrylic	ABS				
6.5 N/cm	60 oz/in	350 Acrylic	Polycarbonate (PC)				
4.8 N/cm	44 oz/in	350 Acrylic	Polypropylene (PP)				
4.3 N/cm	39 oz/in	Silicone	ABS				
4.5 N/cm	42 oz/in	Silicone	Polycarbonate (PC)				
4.4 N/cm	40 oz/in	Silicone	Polypropylene (PP)				
4.4 N/cm	40 oz/in	Silicone	Stainless Steel	15	min	23C	73F
4.5 N/cm	42 oz/in	Silicone	Stainless Steel	72	hr	23C	73F
5.2 N/cm	48 oz/in	Silicone	Stainless Steel	72	hr	70C	158F
7.7 N/cm	71 oz/in	350 Acrylic	Stainless Steel	15	min	23C	73F
10.1 N/cm	93 oz/in	350 Acrylic	Stainless Steel	72	hr	23C	73F
13.2 N/cm	121 oz/in	350 Acrylic	Stainless Steel	72	hr	70C	158F

Property: 180° Peel Adhesion  
Method: ASTM D3330

## Typical Performance Characteristics (continued)

Static Shear	Test Name	Test Condition
6090 min	Faceside	1000 g @ Room Temperature
>10,000 min	Backside	1000 g @ Room Temperature
>10,000 min	Faceside	500 g @ 70°C (158°F)
>10,000 min	Backside	500 g @ 70°C (158°F)

Property: Static Shear  
Method: ASTM D3654  
notes: 0.5 in<sup>2</sup> sample size

Property	Values		Test Condition
Short Term Temperature Resistance	350 °F	177 °C	Short Term (minutes, hour)
Long Term Temperature Resistance	250 °F	121 °C	Long Term (day, weeks)

## Available Sizes

Property	Values	
Note	Subject to Minimum Order Requirements	
Minimum Available Width	6.35 mm	1/4 in
Maximum Available Width	965 mm	38 in
Normal Slitting Tolerance	±0.8 mm	±1/32 in
Core Size (ID)	76.2 mm	3 in

Maximum Length		Width
32.9 m	36 yd	1/4 in to 3/8 in widths
98.9 mm	108 yd	1 to 38 in

Property: Maximum Length

## Electrical and Thermal Properties

Property	Values	Method	Notes	Test Condition	Test Name
Dielectric Strength	8000 V	ASTM D1000	RMS Voltage/Thickness		
Volume Resistivity	$3.4 \times 10^{15} \Omega\text{-cm}$	ASTM D257		Room Temperature	

Table continued on next page

**Electrical and Thermal Properties (continued)**

Property	Values	Method	Notes	Test Condition	Test Name
Surface Resistivity	$7.4 \times 10^{15} \Omega\text{-cm}$	ASTM D257		Room Temperature	350 Acrylic
Surface Resistivity	$2.6 \times 10^{15} \Omega\text{-cm}$	ASTM D257		Room Temperature	Silicone

**Handling/Application Information****Application Examples**

- Applications where bonding Silicone Rubber to low surface energy materials is necessary.

**Application Techniques**

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improves bond strength.

To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.\* Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

\*Note: Carefully read and follow the manufacturer's precautions and directions for use when working with solvents. These cleaning recommendations may not be in compliance with the rules of certain air quality management districts in California; consult applicable rules before use.

**Application Equipment**

To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, Lamination Techniques for Converters of Laminating Adhesives (70-0704-1430-8).

For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

**Storage and Shelf Life**

Store in original cartons at 70°F (21°C) and 50% relative humidity.

If stored under proper conditions, product retains its performance and properties for 24 months from date of manufacture.

**Trademarks**

3M is a trademark of 3M Company.

**References**

Property	Values
3m.com Product Page	<a href="https://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M-Double-Coated-Tape-9731/?N=5002385+3293242257&amp;rt=rud">https://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M-Double-Coated-Tape-9731/?N=5002385+3293242257&amp;rt=rud</a>
Safety Data Sheet SDS	<a href="https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=9731">https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=9731</a>

# 3M™ Double Coated Tape 9731

## Family Group

	9731	9731RW
Long Term Temperature Resistance (°F) Test Condition: Long Term (day, weeks)	250	250
Adhesive Type Test Name: Backside	Silicone Adhesive	350 Acrylic Adhesive
Long Term Temperature Resistance (°C) Test Condition: Long Term (day, weeks)	121.1111	121.1111
Short Term Temperature Resistance (°C) Test Condition: Short Term (minutes, hour)	176.6667	176.6667
Adhesive Thickness (mm) Test Name: Backside	0.07	0.041
Liner Color Test Name: Primary	Tan	Clear
Adhesive Type Test Name: Faceside	350 Acrylic Adhesive	Silicone Adhesive
Adhesive Thickness (mm) Test Name: Faceside	0.041	0.07
Liner Color Test Name: Secondary	Clear	Tan
Total Tape Thickness (mm)	0.14	0.14
Carrier Thickness (mm)	0.025	0.025
Adhesive Type	Silicone	Silicone
Adhesive Carrier	Clear PET (Polyester)	Clear PET (Polyester)
Liner	PCK	PCK
Primary Liner Type	58# Polycoated Kraft	Fluoropolymer non-Silicone
Secondary Liner Type	Fluoropolymer non-Silicone	Polycoated Kraft
Liner Thickness (mm)	0.17	0.07
Primary Liner Thickness (mm)	0.17	0.07
Secondary Liner Thickness (mm)	0.07	0.17

## ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

## Recognition/Certification

MSDS: 3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, these products should not present a health and safety hazard. However, use or processing of these products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.

## Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

